



# 3M™ Ultra Conformable Flashing Tape 3015UC

Last Revision Date: June, 2018

## Product Description

3M™ Ultra Conformable Flashing Tape 3015UC is a proprietary 3M detailing tape designed for the commercial construction market to be used in conjunction with a 3M Commercial Air Barrier System. It is constructed with a unique 3M backing that allows up to 370% elongation in multiple directions, enabling contractors to detail windows and other complex penetrations up to 40% faster by not having to cut and splice multiple pieces of tape.

3M acrylic adhesive allows the application of 3M™ Ultra Conformable Flashing Tape 3015UC at temperatures as low as 0°F and as high as 150°F. 3M Ultra Conformable Flashing Tape 3015UC can be exposed to UV sunlight for up to 12 months. It is repositionable, yet will adhere to and accept adhesion from most common building substrates per criteria of AAMA 711-13 using test method ASTM C-794.



## Product Features

- Provides internal strength and durability
- Nail Sealability: Passes ASTM E331/547 per AAMA 711-13, Annex both before and after thermal cycling.
- Strong multi-directional tape stretches and conforms to difficult areas
- Easy, fast and hassle-free installation
- Resists UV exposure for up to 12 months
- Translucent for visual inspection
- Compatible with the most common building and construction substrates







## Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

## Typical Physical Properties

Property	Values	Additional Information
Adhesive Type	High Performance Acrylic	
Color	Translucent Grey	
Total Tape Thickness (mil)	38 mil	View 
Test Method: ASTM D3652		
Total Tape Thickness (mm)	0.97 mm	View 
Test Method: ASTM D3652		

## Typical Performance Characteristics

Property	Values	Additional Information
90° Peel Adhesion	254 N/cm	View 
<p>Test Method: ASTM D3330</p> <p>Dwell/Cure Time: 24.0  Dwell Time Units: hr  Temp C: 23C  Temp F: 72F  Environmental Condition: 50%RH  Substrate: Stainless Steel  Backing: 5 mil Aluminum Foil</p> <p>Notes: 12 in/min (300 mm/min)</p>		
90° Peel Adhesion	22 lb/in	View 
<p>Test Method: ASTM D3330</p> <p>Dwell/Cure Time: 24.0  Dwell Time Units: hr  Temp C: 23C  Temp F: 72F  Environmental Condition: 50%RH  Backing: 5 mil Aluminum Foil</p> <p>Notes: 12 in/min (300 mm/min)</p>		
90° Peel Adhesion	255 N/cm	View 
<p>Test Method: ASTM D3330</p> <p>Dwell/Cure Time: 24.0  Dwell Time Units: hr  Temp C: 23C  Temp F: 72F  Environmental Condition: 50%RH  Substrate: Concrete Based Material</p> <p>Notes: 12 in/min (300 mm/min)</p>		
90° Peel Adhesion	23 lb/in	View 
<p>Test Method: ASTM D3330</p> <p>Dwell/Cure Time: 24.0  Dwell Time Units: hr  Temp C: 23C  Temp F: 72F  Environmental Condition: 50%RH  Substrate: Concrete Based Material</p> <p>Notes: 12 in/min (300 mm/min)</p>		
90° Peel Adhesion	255 N/cm	View 
<p>Test Method: ASTM D3330</p> <p>Dwell/Cure Time: 24.0  Dwell Time Units: hr  Temp C: 23C  Temp F: 72F  Environmental Condition: 50%RH  Substrate: OSB</p> <p>Notes: 12 in/min (300 mm/min)</p>		
90° Peel Adhesion	23 lb/in	View 
<p>Test Method: ASTM D3330</p>		

Dwell/Cure Time: 24.0  
 Dwell Time Units: hr  
 Temp C: 23C  
 Temp F: 72F  
 Environmental Condition: 50%RH  
 Substrate: OSB

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

255 N/cm

View 

Test Method: ASTM D3330

Dwell/Cure Time: 24.0  
 Dwell Time Units: hr  
 Temp C: 23C  
 Temp F: 72F  
 Environmental Condition: 50%RH  
 Substrate: Wood

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

23 lb/in

View 

Test Method: ASTM D3330

Dwell/Cure Time: 24.0  
 Dwell Time Units: hr  
 Temp C: 23C  
 Temp F: 72F  
 Environmental Condition: 50%RH  
 Substrate: Wood

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

\*48.6 N/cm

View 

Test Method: ASTM D3330

Dwell/Cure Time: 24.0  
 Dwell Time Units: hr  
 Temp C: 23C  
 Temp F: 72F  
 Environmental Condition: 50%RH  
 Substrate: Exterior Grade Gypsum Board

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

\*4.3 lb/in

View 

Test Method: ASTM D3330

Dwell/Cure Time: 24.0  
 Dwell Time Units: hr  
 Temp C: 23C  
 Temp F: 72F  
 Environmental Condition: 50%RH  
 Substrate: Exterior Grade Gypsum Board

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

372.8 N/cm

View 

Test Method: ASTM D3330

Dwell/Cure Time: 168.0  
 Dwell Time Units: hr  
 Temp C: 23C  
 Temp F: 72F  
 Environmental Condition: 50%RH  
 Substrate: Stainless Steel

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

33 lb/in

View 

Test Method: ASTM D3330

Dwell/Cure Time: 168.0  
Dwell Time Units: hr  
Temp C: 23C  
Temp F: 72F  
Environmental Condition: 50%RH  
Substrate: Stainless Steel

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

355.9 N/cm

View 

Test Method: ASTM D3330

Dwell/Cure Time: 168.0  
Dwell Time Units: hr  
Temp C: 23C  
Temp F: 72F  
Environmental Condition: 50%RH  
Substrate: Concrete Based Material

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

31.5 lb/in

View 


Test Method: ASTM D3330

Dwell/Cure Time: 168.0  
Dwell Time Units: hr  
Temp C: 23C  
Temp F: 72F  
Environmental Condition: 50%RH  
Substrate: Concrete Based Material

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

279.1 N/cm

View 

Test Method: ASTM D3330

Dwell/Cure Time: 168.0  
Dwell Time Units: hr  
Temp C: 23C  
Temp F: 72F  
Environmental Condition: 50%RH  
Substrate: OSB

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

24.7 lb/in

View 

Test Method: ASTM D3330

Dwell/Cure Time: 168.0  
Dwell Time Units: hr  
Temp C: 23C  
Temp F: 72F  
Environmental Condition: 50%RH  
Substrate: OSB

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

355.9 N/cm

View 

Test Method: ASTM D3330


Dwell/Cure Time: 168.0  
Dwell Time Units: hr  
Temp C: 23C  
Temp F: 72F

Environmental Condition: 50%RH  
Substrate: Wood

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

31.5 lb/in

View 

Test Method: ASTM D3330

Dwell/Cure Time: 168.0  
Dwell Time Units: hr  
Temp C: 23C  
Temp F: 72F  
Environmental Condition: 50%RH  
Substrate: Wood

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

\*54.2 N/cm

View 


Test Method: ASTM D3330

Dwell/Cure Time: 168.0  
Dwell Time Units: hr  
Temp C: 23C  
Temp F: 72F  
Environmental Condition: 50%RH  
Substrate: Exterior Grade Gypsum Board

Notes: 12 in/min (300 mm/min)

90° Peel Adhesion

\*4.8 lb/in

View 

Test Method: ASTM D3330

Dwell/Cure Time: 168.0  
Dwell Time Units: hr  
Temp C: 23C  
Temp F: 72F  
Environmental Condition: 50%RH  
Substrate: Exterior Grade Gypsum Board

Notes: 12 in/min (300 mm/min)

Tensile Strength


0.029 MPa

View 

Test Method: ASTM D412

Tensile Strength

4.2 lb/in<sup>2</sup>

View 

Test Method: ASTM D412

Elongation at Break

≥ 300 %

View 

Test Method: ASTM D412

## Storage and Shelf Life

Store under normal conditions of 60° to 80°F (16° to 27°C) and 40 to 60% relative humidity in the original carton.  
To obtain best performance, use this product within 24 months from date of manufacture.

## Bottom Matter

3M  
 Industrial Adhesives and Tapes Division  
 3M Center, Building 225-3S-06  
 St. Paul, MN 55144-1000  
 800-362-3550

## Trademarks

---

3M is a trademark of 3M Company.

## Handling/Application Information

---

### Application Examples

- Sealing around rough openings and joints in commercial building applications
- Sealing of through wall flashing penetrations such as ducts, conduits, cables and pipes
- Conforms to all dimensions of through wall penetrations openings within building envelopes such as around electrical cables, chimneys etc. to prevent air/moisture and water intrusion
- Recommended for construction types 1-4

### Application Techniques

- Fill gaps and cracks exceeding ¼" width with 3M™ Polyurethane Sealant 540 or 3M™ Polyurethane Construction Sealant 525, and tool the surface flush and smooth.
- Fill gaps exceeding ½" width with closed cell foam backer rod, seal with 3M™ Polyurethane Sealant 540 or 3M™ Polyurethane Construction Sealant 525, and tool the surface flush and smooth.

### Directions for Use

- To obtain the best adhesion, 3M™ Ultra Conformable Flashing Tape 3015UC should be applied when temperatures range from 0°F (-18°C) up to 150°F (66°C) over clean surfaces that are free from dirt and debris and have not absorbed water.
- Surfaces should be free of any damaged, unsupported areas, sharp protrusions or voids.
- Concrete must be cured a minimum of 7 days before application.
- While it can be applied as low as 0°F (-18°C) surfaces must be clear of snow, ice or frost.
- Must be lapped a minimum of 2" with air barrier.
- Adheres to most common building materials. For difficult-to-stick-to surfaces, test adhesion before application. If needed, apply 3M™ Hi-Strength 90 Spray Adhesive, 3M™ Hi-Strength 94ET Spray Adhesive, 3M™ Holdfast 70 Spray Adhesive or 3M™ Fastbond™ Contact Adhesive 30NF to prime the substrate prior to applying the membrane. Products are available as either an aerosol or cylinder spray adhesive.

## References

---

Property	Values
3m.com Product Page	<a href="https://www.3m.com/3M/en_US/p/d/b5005036057/">https://www.3m.com/3M/en_US/p/d/b5005036057/</a>
Safety Data Sheet SDS	<a href="https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&amp;msdsLocale=en_US&amp;co=ptn&amp;q=3015UC">https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&amp;msdsLocale=en_US&amp;co=ptn&amp;q=3015UC</a>

## ISO Statement

---

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

## Information

---

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a



particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit [www.3M.com](http://www.3M.com).